



MATTE TRANSLUCENT FILM

DECORATIVE FILMS FOR PRIVACY & DISTINCTION



HanitaTek
Window Films

MATTE TRANSLUCENT FILM

MATTE TRANSLUCENT FILMS

SolarZone's™ 2 mil matte translucent films are ideal for enhancing the functionality and appearance of glass—whether to provide privacy, delineate space, disguise unattractive features, or provide graphic impact.

Matte translucent films can also be used to make a bold statement. Graphic accents, company logos and icons can all be created easily.

Matte translucent films are available in either white or matte silver, in 2 mil with a PS adhesive. Matte translucent white is also offered—combined with 5 or 12 mil safety/security film—for privacy and personal safety in retail, bathroom and office space applications.

All matte translucent films are suitable for installation on clear or tinted single-and double-pane glazing.

THE ATTRACTIVE, PRACTICAL SOLUTION THAT PROVIDES:

- Cost-effective alternative to sandblasting
- Privacy
- Diffused light
- Graphic interest
- Glass visibility
- Camouflage
- Increased safety

IDEAL FOR:

- Offices and clinics
- Conference rooms
- Bathrooms
- Partitions
- Corridors
- Doors
- Graphics
- Retail display



S O L A R Z O N E

MATTE TRANSLUCENT FILM



SOLARZONE™

Optical & Solar Properties	Matte 2 Mil Translucent	Matte Silver 20
Visible Light Transmitted	69%	15%
Total Solar Energy Reflected	18%	58%
Total Solar Energy Absorbed	19%	30%
Total Solar Energy Transmitted	63%	12%
Visible Light Reflected	18%	56%
UV Radiation Rejected	88%	97%
Shading Coefficient	0.79	0.24
Emissivity	0.83	0.67
Total Solar Energy Rejected	29%	78%

SAFETYZONE™

Optical & Solar Properties	5 Mil Matte	12 Mil Matte
Visible Light Transmitted	55%	48%
Visible Light Reflected	14%	19%
UV Radiation Rejected	94%	97%
Total Solar Energy Reflected	14%	19%
Total Solar Energy Transmitted	57%	48%
Total Solar Energy Absorbed	29%	33%
Shading Coefficient	0.75	0.67
Total Solar Energy Rejected	33%	40%

All solar performance data is based on film being applied to the inside of 1/4 inch clear monolithic annealed glass. All data reported has been measured, calculated and reported in accordance with ASTM, ASHRAE and AIMCAL standards. The data is subject to variations within accepted industry standards.

HANITATEK Tel: 800.660.5559 | www.hanitatek.com

