

SOLARZONE QUICK REFERENCE CHART

| Film Type | Visible Light Transmitted | Total Solar Energy Rejected | Visible Light Reflected | UV Radiation Rejected | Shading Coefficient |
|---------------------------------|---------------------------|-----------------------------|-------------------------|-----------------------|---------------------|
| Optitune 15 | 12% | 80% | 50% | 99% | 0.25 |
| Optitune 30 | 31% | 64% | 28% | 99% | 0.42 |
| Optitune 40 | 40% | 55% | 20% | 99% | 0.52 |
| Optitune 55 | 53% | 42% | 12% | 99% | 0.64 |
| Cold Steel 20 | 19% | 68% | 19% | 99% | 0.35 |
| Cold Steel 35 | 35% | 56% | 12% | 99% | 0.48 |
| Cold Steel 50 | 47% | 51% | 14% | 99% | 0.57 |
| Cold Steel 70 | 66% | 34% | 9% | 99% | 0.76 |
| Silver 20 | 17% | 77% | 55% | 99% | 0.27 |
| Silver 35 | 31% | 67% | 42% | 99% | 0.37 |
| Silver 50 | 46% | 55% | 27% | 95% | 0.50 |
| Silver/Bronze 15 | 13% | 71% | 18% | 99% | 0.33 |
| Solar Bronze 20 | 20% | 77% | 36% | 99% | 0.27 |
| Solar Bronze 35 | 35% | 65% | 26% | 97% | 0.39 |
| Solar Bronze 50 | 50% | 54% | 17% | 97% | 0.53 |
| Matte 2 Mil Translucent | 69% | 29% | 18% | 88% | 0.79 |
| Matte Silver 20 | 15% | 78% | 56% | 97% | 0.24 |
| Black Out Film | 1% | 67% | 8% | 99% | 0.38 |
| 6 Mil Anti-Graffiti Film | 85% | 19% | 11% | 93% | 0.92 |

All solar performance data is based on film being applied to the inside of 1/4 inch clear monolithic annealed glass. All data reported has been measured, calculated and reported in accordance with ASTM, ASHRAE and AIMCAL standards. The data is subject to variations within accepted industry standards.